

DOWSIL™ 995 Silicone Structural Sealant

Features

- One-component, neutral curing silicone, curing to form a flexible elastomeric rubber
- Widely specified for use in conjunction with protective window films, which provide increased impact resistance and help to capture and absorb impact energy; maintains positive adhesion when window frames bend and twist under a range of stresses, like bomb blasts and hurricane conditions, thus reducing the potential for broken glass being blown from the frames
- High tensile strength and excellent mechanical properties, making it ideal for structural bonding
- Offers excellent unprimed adhesion to most common building substrates such as glass, reflective glass, anodized aluminium and granite
- Excellent weatherability – UV stable and high performance across a wide temperature range
- Meets the newly developed European standards for structural glazing applications as developed by EOTA and SNJF – VEC



Applications

DOWSIL™ 995 Silicone Structural Sealant is a one component, neutral curing, elastomeric sealant specifically formulated for structural glazing and protective glazing applications.

Technical characteristics		
	Unit	Value
Application temperature range	°C	+5 to +40
Service temperature range	°C	-50 to +100
Specific gravity		1.34
Working time	minutes	10-20
Tack-free time	minutes	130
Full adhesion	days	21
Flow/sag/slump	mm	0.1
Movement capability	%	±50
Storage temperature	°C	<30
Usable life	months	12

Contact us

Dow is collaborating with industry professionals around the world to develop solutions to improve the energy efficiency of buildings for a more comfortable environment. Learn more about Dow's full range of High Performance Building Solutions by visiting us online at consumer.dow.com/construction.

Dow has sales offices, manufacturing sites and science and technology laboratories around the globe. Find local contact information at consumer.dow.com/ContactUs.

Image: AdobeStock_219122699

LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DOW SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.

DOW DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.

®™ Trademark of The Dow Chemical Company ("Dow") or an affiliated company of Dow

© 2019 The Dow Chemical Company. All rights reserved

S2D 92424/E27145

Form No. 62-1266-01 E